

A vibrant, high-angle photograph of a tropical forest. A waterfall cascades down a rocky ledge in the center-left, feeding into a stream that flows over dark, wet rocks in the foreground. The forest is dense with various shades of green, from deep emerald to bright lime green, suggesting a rich, humid environment. The lighting is soft and diffused, creating a misty atmosphere.

JM

Johnson Matthey
Inspiring science, enhancing life

Lagerliste Lote / Liste de stock disponible soudure

		Artikel Nr No. d'article	Schmelzintervall Intervalle de fusion
Au 750 3N	weich/faible	5.1182	710 - 750
Au 750 3N	mittel/moyen	5.1183	730 - 765
Au 750 3N	hart/dur	5.1184	760 - 820
Au 917		5.1567	865 - 890
Au 588 WG	mittel/moyen	5.1186	705 - 720
Au 750 WG	mittel/moyen	5.3093	835 - 885
Au 750 WG	hart/dur	5.3092	950 - 1010
Au 750 5N	weich/faible	5.1234	690 - 790
Au 750 5N	mittel/moyen	5.1200	690 - 815

		Artikel Nr No. d'article	Schmelzintervall Intervalle de fusion
Platin	extra weich/faible	5.1188	935 - 955
Platin	weich/faible	5.1189	1010 - 1030
Platin	hart/dur	5.1191	1420 - 1445
Silber	weich/faible	5.0104	705 - 723
Silber	mittel/moyen	5.0105	720 - 765
Silber	hart/dur	5.0106	745 - 778
Palladium	Für Pd 950 Legierungen empfehlen wir unsere Pt-Lote Pour les alliages Pd 950 nous recommandons les soudures Pt		

Dose / boîte		Artikel Nr No. d'article	Gramm
LT Flux	Pulver / poudre	5.1221	50
HW Flux	Pulver / poudre	5.1222	50
HT Flux	Pulver / poudre	5.1202	50