

A vibrant, high-angle photograph of a tropical forest. A waterfall cascades down a rocky cliff in the center-left, feeding into a stream that flows over dark, wet rocks in the foreground. The forest is dense with various shades of green, from bright lime to deep forest green. The lighting is soft and diffused, creating a misty atmosphere. The overall scene is serene and natural.

JM

Johnson Matthey
Inspiring science, enhancing life

Stock list braze

		Artikel Nr No. d'article	Schmelzintervall Intervalle de fusion
Au 750 3N	weich/faible	5.1182	710 - 750
Au 750 3N	mittel/moyen	5.1183	730 - 765
Au 750 3N	hart/dur	5.1184	760 - 820
Au 917		5.1567	865 - 890
Au 588 WG	mittel/moyen	5.1186	705 - 720
Au 750 WG	mittel/moyen	5.3093	835 - 885
Au 750 WG	hart/dur	5.3092	950 - 1010
Au 750 5N	weich/faible	5.1234	690 - 790
Au 750 5N	mittel/moyen	5.1200	690 - 815

		Item number	Melting range
Platin	extra soft	5.1188	935 - 955
Platin	soft	5.1189	1010 - 1030
Platin	hard	5.1191	1420 - 1445
Silber	soft	5.0104	705 - 723
Silber	medium	5.0105	720 - 765
Silber	hard	5.0106	745 - 778
Palladium	for Pd 950 alloys we recommend our Pt-brazures		

Container		Item number	Gram
LT Flux	powder	5.1221	50
HW Flux	powder	5.1222	50
HT Flux	powder	5.1202	50